

This listing of claims replaces all previous versions or listings of claims previously presented.

Listing of Claims

B12

1. (Amended herein) An insulating composition for an electric power cable which comprises a crosslinkable ethylene polymer, characterized in that the ethylene polymer is a multimodal ethylene copolymer obtained by coordination catalyzed polymerization of ethylene and at least one other alpha-olefin in at least one stage, said multimodal ethylene copolymer having a density of 0.890-0.940 g/cm³, a MFR₂ of 0.1-10 g/10 min, a MWD of 3.5-8, a melting temperature of at most 125°C, and a comonomer distribution as measured by TREF, such that the fraction of copolymer eluted at a temperature higher than 90°C does not exceed 5% by weight, and said multimodal ethylene copolymer including an ethylene copolymer fraction selected from (a) a low molecular weight ethylene copolymer having a density of 0.900-0.950 g/cm³ and a MFR₂ of 25-500 g/10 min, and (b) a high molecular weight ethylene copolymer having a density of 0.870-0.940 g/cm³ and a MFR₂ of 0.01-3 g/10 min.

2. Cancelled herein

3. (Previously Amended) An insulating composition as claimed in claim 1, wherein the multimodal ethylene copolymer has a viscosity of 2500-7500 Pa.s at 135°C and a shear rate of 10 s⁻¹, 1000-2200 Pa.s at 135°C and a shear rate of 100 s⁻¹, and 250-400 Pa.s at 135°C and a shear rate of 1000 s⁻¹.

4. (Original) An insulating composition as claimed in claim 3, wherein the multimodal ethylene copolymer has a viscosity of 4000-7000 Pa.s at 135°C and a shear rate of 10 s⁻¹, 1000-2000 Pa.s at 135°C and a shear rate of 100 s⁻¹, and 300-350 Pa.s at 135°C and a shear rate of 1000 s⁻¹.

5. (Previously Amended) An insulating composition as claimed in claim 1, wherein the comonomer of the copolymer is at least one member selected from the group consisting of propylene, 1-butene, 4-methyl-1-pentene, 1-hexene, and 1-octene.

6. (Previously Amended) An insulating composition as claimed in claim 1, wherein the MWD is 4-5.

B12
7. (Previously Amended) An insulating composition as claimed in claim 1, wherein the multimodal ethylene copolymer is a bimodal ethylene copolymer comprising 30-60 % by weight of a low molecular weight ethylene copolymer fraction and 70-40 % by weight of a high molecular weight ethylene copolymer fraction.

8. (Previously Amended) An insulating composition as claimed in claim 1, wherein the multimodal ethylene copolymer includes a low molecular weight ethylene copolymer fraction having a density of 0.900-0.950 g/cm³ and a MFR₂ of 50-100 g/10 min.

9. (Amended herein) An electric power cable comprising a conductor surrounded by an inner semiconducting layer, an insulating layer, and an outer semiconducting layer, characterized in that the insulating layer comprises a crosslinked ethylene copolymer obtained by coordination catalyzed polymerization of ethylene and at least one other alpha-olefin in at least one stage, said multimodal ethylene copolymer having a density of 0.890--0.940 g/cm³, a MFR₂ of 0.1-10 g/10 min, a MWD of 3.5-8, a melting temperature of at most 125°C, and a comonomer distribution as measured by TREF, such that the fraction of copolymer eluted at a temperature higher than 90°C does not exceed 5% by weight, and said multimodal ethylene copolymer including an ethylene copolymer fraction selected from (a) a low molecular weight ethylene copolymer having a density of 0.900-0.950 g/cm³ and a MFR₂ of 25-500 g/10 min, and (b) a high molecular weight ethylene copolymer having a density of 0.870-0.940 g/cm³ and a MFR₂ of 0.01-3 g/10 min.